



Technical Notes

Details vary according to desired results.

CLAY

A stoneware mixture – Potterycraft & Creaton 592.

OXIDES

A solution of copper carbonate or powdered copper oxide.

FIRINGS

Reduction firing; sometimes once fired at Cone 02, or bisque fired at Cone 06 with glaze firing at 002.